



NuovoCoat Colour Coat Hydro WB Paint



1000 ml +
120-170 ml



32-38" FC 4
at 20° C




Ø1,2-1,4 mm
4 Atm

N° of coats: 2-3



Air drying at 20° C
Handling: 30-40 min.
Through-drying: 24 h
Low bake at 60° C
60 min.



+ 5° – +35° C

DESCRIPTION

One-pack water-borne acrylic topcoat

USE

Used for painting metal manufactured items in General Industry, industrial vehicles, Agriculture, Construction and Earthmoving (A.C.E.).

CHARACTERISTICS

- Easy to apply
- Good aesthetical aspect
- Good mechanical characteristics
- Fast drying
- Satisfactory direct adhesion on steel (it does not contain any active anticorrosive pigments, anticorrosive power due to barrier effect), cast iron
- Low V.O.C.

Substrate Preparation

Degreasing with NuovoCoat uPVC cleaner or with suitable surface-active agents

Application

Spraying.

Mixing ratio:

Hydro WB Colour Coat
NC-089 Desalted Water

weight	volume
1000 g	1000 ml
100-150 g	120-170 ml

Spray viscosity at 20° C: 32-38" FORD Cup 4
Ø Air cap: conventional: 1,2-1,4 mm
Air pressure: conventional 4 Atm

Master Finish by APS. Unit 19 Europa Park, Dee View Boulevard, Chester CH1 4NP.

www.masterfinish.co.uk - Tel 01244 375029

N° of coats: 2-3
Recommended film thickness: 30-40 µ
Theoretical coverage: 5.2 – 5.9 m² for 1l mixture at 40 µ
Application conditions: temperature 15-30°C relative humidity 30-80%

DIR 2004/42/CE: Topcoat IIB/d – VOC ready for use 420 g/l
This product ready for use contains at most 270 g/l VOC (without water)

DIR 2004/42/CE: Interior/exterior trim and cladding paints of wood, metal –
EU limit value for this product (cat. d/BA): 130 g/l (2010) of VOC product ready for use
This product ready for use contains at most 62 g/l VOC (with water)

Drying Time

Air drying at 20° C:

Dust-free: 15-20 min.
Handling: 30-40 min.
Through-drying: 24 h

Low bake at 60°C:

60 min.

Observations

Keep away from frost. Storage temperature: from +5° to +35°C

TECHNICAL DATA SHEET N° 0005
UPDATED 04/2026

All information contained in this data sheet is the result of carefully controlled tests and is correct to the best of Master Finish's knowledge at the time of issue. Since conditions of use are beyond the control of the manufacturer, information contained herein is without warranty, implied or otherwise, and final determination of the suitability of any information or material for the use contemplated and the manner of use is the sole responsibility of the user. FOR PROFESSIONAL USE ONLY.

Master Finish by APS. Unit 19 Europa Park, Dee View Boulevard, Chester CH1 4NP.

www.masterfinish.co.uk - Tel 01244 375029