



NuovoCoat uPVC & Composite Hydro WB Paint



1000 ml +
150 ml +
100-300 ml

Maximum time of use
at 20° C: 2 h




20-30° FC 4
at 20° C



Ø 1.2-1,4 mm
Pressure 3.5-4 Atm
N° of coats: 2+2



Air drying at 20° C
Flash-off 30 min.
Through-drying
Low bake at 80° C
40 min.



+5° - +35° C

Description

Waterbased topcoat with direct adhesion on PC, PVC.

Use

Topcoat with direct adhesion for applications onto uPVC and composite substrates

Characteristics

- Easy application
 - Good scratch and abrasion resistance
 - Good mechanical characteristics
 - High light and weather resistance
 - Very good coverage and hiding power
 - Quick drying
 - Low V.O.C.
-

Substrate Preparation

Degreasing with NuovoCoat uPVC cleaner or with suitable surface-active agents.

Dust removal and blowing with de-ionized air.

Direct application on PC, PVC

On other substrates use special primers.

Due to the possible different composition of PVC substrates proposed by the market, it is recommended to always test adhesion, possibly according to the Standard ASTM D 3359 (B), prior to proceeding with the final application.

Application

Spraying.

Master Finish by APS. Unit 19 Europa Park, Dee View Boulevard, Chester CH1 4NP.

www.masterfinish.co.uk - Tel 01244 375029

Mixing ratio:

Hydro WB Paint
NC-016 Hydro WB Hardener
NC-089 Desalted Water

Weight / Volume
1000 parts
150 parts
100-300 parts

Note: We recommend adding the hardener during the mixing process until complete homogenisation. Thin after completion. Where this is not possible, add the hardener immediately and stir vigorously, again adding thinner after completion.

Maximum time of use at 20 °C: 2 h
Spray viscosity at 20°C: 20-30" FC 4
Ø Air cap: 1.2- 1.4 mm
Air pressure: 3.5-4 Atm
N° of coats: 2+2
Recommended film thickness: 35-45 µ
Theoretical coverage: 1 l mixture = 6 m²/l at 45 µ
Application conditions: Temperature: 20-25°C relative humidity: 50-70%

**DIR 2004/42/CE: Interior/exterior trim and cladding paints of wood, metal –
EU limit value for this product (cat. d/BA): 130 g/l (2010) of VOC product ready for use
This product ready for use contains at most 54 g/l VOC (with water)**

Drying Time

Flash-off: 30 min. at 20°C
Low bake: 40 min. at 80°C

Observations

Keep away from frost. Storage temperature: from +5° to +35°C

**TECHNICAL DATA SHEET N° 0001
UPDATED 04/2026**

All information contained in this data sheet is the result of carefully controlled tests and is correct to the best of Master Finish knowledge at the time of issue. Since conditions of use are beyond the control of the manufacturer, information contained herein is without warranty, implied or otherwise, and final determination of the suitability of any information or material for the use contemplated and the manner of use is the sole responsibility of the user. FOR PROFESSIONAL USE ONLY.

**Master Finish by APS. Unit 19 Europa Park, Dee View Boulevard, Chester CH1 4NP.
www.masterfinish.co.uk - Tel 01244 375029**