



Colour Coat Interior Paint



1000 ml +
700-800 ml



16-17" DIN 4
at 20° C



Ø 1,4-1,6 mm
4 Atm
N° of coats: 2-3



Air drying at 20° C
Handling: 45 min.
Through-drying: 3 h

Description

Industrial nitro-combi enamel.

Use

Nitro cellulose enamel for general industrial use including machines, metallic shelves, tools and general ferrous substrates.

Characteristics

- Fast drying.
 - Good adhesion directly to steel (the product does not contain any anticorrosive pigments; steel protection due to barrier-effect).
 - Good aesthetical appearance.
-

Substrate Preparation

Degreasing with Hydro Coat WB Degreaser HC095

APPLICATION

Spray & brush application

Mixing ratio:

Solvent Coat Interior Paint
SC-824 Universal Thinners Slow

weight and volume

1000 parts
700-800 parts

Spray viscosity at 20°C: 16 - 17" DIN4

Ø Air cap: 1.4 - 1.6 mm

Air pressure: 4 Atm

Number of coats: 2 - 3

Film thickness: 25 – 35 µ

Theoretical coverage: 1 l mixture = 5,5 – 6 m² at 25 µ

1 kg mixture = 6 m² at 25 µ

V.O.C. of the product ready for use: ~ 760 g/l

Drying Time

Air drying at 20°C:

Dust-free: 5 min.

Handling: 45 min.

Through-drying: 3 hours

TECHNICAL DATA SHEET N° 0006

UPDATED 04/2026

All information contained in this data sheet is the result of carefully controlled tests and is correct to the best of Master Finish's knowledge at the time of issue. Since conditions of use are beyond the control of the manufacturer, information contained herein is without warranty, implied or otherwise, and final determination of the suitability of any information or material for the use contemplated and the manner of use is the sole responsibility of the user. FOR PROFESSIONAL USE ONLY.